

## OK Tigrod 5356

OK Tigrod 5356 is the most widely used welding alloy and can be classified as a general purpose type filler alloy. OK Tigrod 5356 is typically chosen because of its relatively high shear strength. The 5XXX alloy base material, welded with OK Tigrod 5356, with a weld pool chemistry greater than 3 % Mg and service temperatures in excess of 65 °C are susceptible to stress corrosion cracking. The alloy is non-heat treatable.

<b>Classifications</b>	JIS Z 3232 : A5356 SFA/AWS A5.10 : R5356 EN ISO 18273 : S Al 5356 (AlMg5Cr(A))
<b>Approvals</b>	ABS : R 5356 CE : EN 13479 CWB : A5.10/A5.10M:2012 ER5356 DB : 61.039.02 JIS : JIS Z 3232 VdTÜV : 04665

<b>Alloy Type</b>	AlMg 5
-------------------	--------

Typical Wire Composition %							
Mn	Si	Cr	Al	Cu	Zn	Fe	Mg
0.13	0.05	0.12	94.560	0.01	0.01	0.13	4.9